

Peninsula Products, Inc.  
3014 W. Palmira Ave., #200  
Tampa, FL 33629  
T: 813-832-4080  
F: 813-832-4202  
www.easyspred.com



...for mortar, grout & plaster

## **EASY-SPRED® FOR POOL PLASTERERS**

Easy-Spred® is an admixture that improves the quality and field properties of portland cement based pool plaster. Easy-Spred® has been used for over 50 years and is packaged for contractor use in 7 lb. bags. Easy-Spred® can be instituted to improve the plaster's flowability, pumpability, workability and cohesiveness. Easy-Spred® also helps reduce drying shrinkage. At the job site, pool plasterers use Easy-Spred® as an ingredient in their marcite or exposed aggregate mixes. Easy-Spred® is also used as an admixture with pre-blended marcite and exposed aggregate finishes.

**Typical Easy-Spred® Swimming Pool Finish Coat:** The following mix gives a beautiful finish with the possibility of less shrinkage. The mix is very plastic which enhances the contractor's workmanship at an economical cost.

6 bags of Marble Dust	100 lb. Bags
4 bags White Portland Cement	94 lb. Bags
1 to 2 bags of Easy-Spred®	7 lb. Bags

**Easy-Spred® as an Admixture:** Easy-Spred® is used as an admixture with pre-blended marcite or exposed aggregate finishes. The recommended dosage rate to use is approximately ½ lb. (8 – 10 fluid ounces by volume) of Easy-Spred® per 80 lb. bag of pre-blended pool finish plaster mix.

**Mixing Instructions:** The following mixing instructions should be followed in order to achieve optimal results:

1. Start mixer. Add approximately 2/3 of total water to be used in batch, then add Easy-Spred® and mix for approximately one (1) minute<sup>A</sup>.
2. Add at least 1/3 of aggregate while mixer running.
3. Add cement while mixer running.
4. Add remaining aggregate and water (to reach desired consistency) while mixer running.
5. Mix until material has desired workability (recommended total mix time is least six (6) minutes).

<sup>A</sup>When using pre-blended pool finish mixes, follow Step 1, then mix pre-blended pool finish mix according to manufacturer's instructions.